



**Cite this article:** Hang T, Chen H-J, Xiao S, Yang C, Chen M, Tao J, Shieh H-p, Yang B-r, Liu C, Xie X. 2017 TiO<sub>2</sub> nanowire-templated hierarchical nanowire network as water-repelling coating. *R. Soc. open sci.*

4: 171431. <http://dx.doi.org/10.1098/rsos.171431>

Received: 23 September 2017

Accepted: 8 November 2017

**Subject Category:**

Chemistry

**Subject Areas:**

materials science/nanotechnology

**Keywords:**

micro-nanoscale structure, hierarchical nanowires, self-cleaning surfaces, superhydrophobic coatings, nanowire thin film

**Author for correspondence:**

Xi Xie

e-mail: [xiexi27@mail.sysu.edu.cn](mailto:xiexi27@mail.sysu.edu.cn)

<sup>†</sup>These authors contributed equally to this work.

This article has been edited by the Royal Society of Chemistry, including the commissioning, peer review process and editorial aspects up to the point of acceptance.

Electronic supplementary material is available online at <https://dx.doi.org/10.6084/m9.figshare.c.3938086>.



# TiO<sub>2</sub> nanowire-templated hierarchical nanowire network as water-repelling coating

Tian Hang<sup>1,†</sup>, Hui-Jiuan Chen<sup>1,†</sup>, Shuai Xiao<sup>1</sup>, Chengduan Yang<sup>1</sup>, Meiwan Chen<sup>2</sup>, Jun Tao<sup>1</sup>, Han-ping Shieh<sup>1,3</sup>, Bo-ru Yang<sup>1</sup>, Chuan Liu<sup>1</sup> and Xi Xie<sup>1</sup>

<sup>1</sup>State Key Laboratory of Optoelectronic Materials and Technologies, School of Electronics and Information Technology; The First Affiliated Hospital of Sun Yat-sen University; Guangdong Province Key Laboratory of Display Material and Technology, Sun Yat-sen University, Guangzhou, China

<sup>2</sup>Institute of Chinese Medical Sciences, University of Macau, Avenida da Universidade, Taipa, Macao SAR, China

<sup>3</sup>Department of Photonics and Display Institute, National Chiao Tung University, Hsinchu, Taiwan, Republic of China

XX, 0000-0001-7406-8444

Extraordinary water-repelling properties of superhydrophobic surfaces make them novel candidates for a great variety of potential applications. A general approach to achieve superhydrophobicity requires low-energy coating on the surface and roughness on nano- and micrometre scale. However, typical construction of superhydrophobic surfaces with micro-nano structure through top-down fabrication is restricted by sophisticated fabrication techniques and limited choices of substrate materials. Micro-nanoscale topographies templated by conventional microparticles through surface coating may produce large variations in roughness and uncontrollable defects, resulting in poorly controlled surface morphology and wettability. In this work, micro-nanoscale hierarchical nanowire network was fabricated to construct self-cleaning coating using one-dimensional TiO<sub>2</sub> nanowires as microscale templates. Hierarchical structure with homogeneous morphology was achieved by branching ZnO nanowires on the TiO<sub>2</sub> nanowire backbones through hydrothermal reaction. The hierarchical nanowire network displayed homogeneous micro/nano-topography, in contrast to hierarchical structure templated by traditional microparticles. This hierarchical nanowire network film exhibited high repellency

to both water and cell culture medium after functionalization with fluorinated organic molecules. The hierarchical structure templated by TiO<sub>2</sub> nanowire coating significantly increased the surface superhydrophobicity compared to vertical ZnO nanowires with nanotopography alone. Our results demonstrated a promising strategy of using nanowires as microscale templates for the rational design of hierarchical coatings with desired superhydrophobicity that can also be applied to various substrate materials.


## 1. Introduction

Self-cleaning surfaces, which possess extraordinary water repellency properties are currently the focus of considerable research [1–3]. They can be applied to the fields including fabric coatings [4,5], anti-biofouling paints [6,7], liquids separation [8,9], self-healing surfaces [10,11] and microfluidic devices [12,13]. One of the most well-known examples of self-cleaning surfaces in nature is the lotus leaf that can effortlessly roll off water drops. The underlying micro-nano hierarchical structure of lotus leaf surface has been revealed to play a key role in the water-repelling properties [14], and a large number of novel self-cleaning surfaces have been inspired by the micro-nano hierarchical structure of lotus leaf surface [1,2,15]. To understand the wetting behaviours of hierarchical surface, the Wenzel and Cassie–Baxter models are generally considered. In the Wenzel state, liquid impregnates the textures on solid surface, and the wetting or non-wetting feature of the solid is amplified due to the increase of the contact area between the liquid and the solid substrate [16]. While in the Cassie–Baxter state, air is trapped between the solid–liquid interface, which stably supports liquid drops sitting on the top of the substrate surface [17]. According to the Cassie–Baxter model, the presence of air pockets provided by the micro-nano hierarchical structure is crucial for superhydrophobic property. So far, it is commonly accepted that both hierarchical micro-nano structure and low surface energy coating on the solid surface are significantly important in achieving superhydrophobic effects. While low surface energy is generally prepared through surface functionalization with highly hydrophobic organic compounds, surface topography of micro-nano structure requires sophisticated fabrication or coating techniques.

To date, most micro-nanoscale structures have been pre-fabricated on substrates by either top-down or bottom-up approaches [13,18–23]. The micro-nanoscale structures were physically attached to the substrate after fabrication, and were further functionalized to be superhydrophobic, forming a robust surface with water-repelling effects. For example, hierarchical Al, Si, ZnO, SiO<sub>2</sub> based surfaces with various surface roughness or surface topographies have been reported with excellent wetting properties [19,24–27]. However, the pre-fabrication process of micro-nanoscale structures and the requirement of physical attachment limit the choices of substrate material. Such approach relies heavily on the intrinsic properties of the used substrate, and can become unsuitable especially for the cases when the substrate material is unable to be fabricated with sub-micro features, or when the substrate material is susceptible or vulnerable to the fabrication process.

On the other hand, superhydrophobic surface produced by coating or drop-casting micro-nanoscale objects on substrate rather than through direct fabrication may get rid of the restriction of substrate types [28]. In such approaches, the micro-nanoscale objects were physically absorbed or coated on the substrate, which allows a variety of substrates to be functionalized with superhydrophobicity regardless of the intrinsic material of substrate. For example, superhydrophobic coatings were fabricated by self-assembling micro- and nano-sized silica spheres [29,30]. Superhydrophobic and superamphiphobic structures were also designed using candle soot as the template [31–33]. Generally the micro-to-nanoscale characteristics in these structures were produced by using microspheres or micropowders as underlying micro-scale templates, followed by decorating with nano-scale objects such as nanoparticles or nanowires (NWs) on the micro-scale templates. However, due to the spherical nature, microparticles have limited contact area with substrate, exhibiting low adhesion with substrate so that they are improper templates for constructing a robust superhydrophobic coating. In addition, when microparticles are drop-casted on the substrate, it is difficult to maintain the surface uniformity. The produced rough surface by stacking microparticles usually has large variations in roughness and uncontrollable defects. As a result, the surface morphology and wettability of the resultant micro-nanoscale structures cannot be well controlled.

Recently, much research has been focused on investigating the wetting behaviours of metal oxide semiconductors such as TiO<sub>2</sub> and ZnO for desirable functional properties [28,33–37]. For instance, Lu *et al.* created an ethanolic suspension of perfluorosilane-coated dual-scale TiO<sub>2</sub> nanoparticles as




**Figure 1.** Schematic of the fabrication and the illustration of water-repelling properties of (a) hierarchical ZnO@TiO<sub>2</sub> NW coating and (b) vertical ZnO NW film.

an excellent water-repellent paint [34]. Campbell *et al.* studied the electrowetting properties of ZnO nanorods with sputtered Teflon. Reversible wettabilities were observed under a threshold voltage of 35 V [35]. Sun *et al.* synthesized ZnO hollow microspheres with robust superhydrophobicity [28]. Although there has been significant progress in fabricating hydrophobic coatings, the possibility of using nanowires as building blocks for superhydrophobic hierarchical structure assembling is worth exploring. In this work, one-dimensional (1D) TiO<sub>2</sub> NWs were employed as microscale templates for the fabrication of micro-nanoscale hierarchical nanowire network to construct superhydrophobic coating. The TiO<sub>2</sub> NWs were coated on substrate by drop-casting method followed by sputtering with a thin ZnO layer. Due to their one-dimensional feature, the TiO<sub>2</sub> NWs of micrometres length formed a robust network film, with each NW sufficiently contacting with the substrate or entangling with other NWs. Secondary ZnO NWs were branched on the TiO<sub>2</sub> nanowire backbones through hydrothermal reaction, which produced nanoscale topography on the TiO<sub>2</sub> NW templates, forming a hierarchical coating of NW network on substrate with homogeneous morphology. The hierarchical surface was further functionalized with fluorinated organic molecules, and exhibited excellent repelling properties against both water and cell culture medium in contrast to flat substrate or vertical ZnO NW substrate. Contrary to the conventional pre-fabrication techniques where substrate materials were limited, our work demonstrated a promising and universal strategy to produce homogeneous micro-nano textured superhydrophobic coating on solid surface that may be applicable for a wide range of substrate materials.

## 2. Results

The schematics shown in figure 1 depict the fabrication procedure of hierarchical ZnO@TiO<sub>2</sub> nanowire film. Initially, TiO<sub>2</sub> NWs were synthesized through hydrothermal approach, where suspension of anatase powders in NaOH aqueous solution was placed in a stainless steel autoclave for reaction at 200°C for 48 h. Sodium titanate precipitate was obtained followed by cation exchange to produce hydrogen titanate NWs, which were further fabricated into TiO<sub>2</sub> NWs through hydrothermal reaction at 180°C for 3 h [38]. The as-synthesized TiO<sub>2</sub> NWs were drop-casted on Si substrate to form a homogeneous NW film on the substrate. The substrate was then heated at 200°C to increase NW film adhesion to the substrate. Thereon, a thin ZnO layer of 50 nm was sputtered on top of the substrate as a seed layer for ZnO branches growth.




**Figure 2.** SEM images of (a) 1D  $\text{TiO}_2$  nanowire film, (b) hierarchical  $\text{ZnO@TiO}_2$  NW film, and (c) vertical ZnO NWs. The right sub-panels show SEM images under different magnifications.

ZnO NWs were grown by hydrothermal method in an aqueous solution containing ZnO precursors (25 mM zinc nitrate hydrate and 25 mM hexamethylenetetramine) at  $80^\circ\text{C}$  [39]. Resultant hierarchical micro-nano structure consisting of ZnO NWs branches on  $\text{TiO}_2$  NW backbone ( $\text{ZnO@TiO}_2$  NWs) was obtained after hydrothermal growth for 2 h. Vertical ZnO NW arrays were also synthesized using similar hydrothermal approach as control samples (ZnO NWs), where a 50 nm ZnO thin layer was sputtered on top of Si substrate, followed by hydrothermal growth of ZnO NWs for 2 h.

Scanning electron microscope (SEM) images of the resultant structures are shown in figure 2.  $\text{TiO}_2$  NWs with diameter of about 100 nm and length more than  $10\ \mu\text{m}$  were homogeneously dispersed on Si substrate (figure 2a). The NWs were randomly oriented and entangled with each other forming a dense network structure. After hydrothermal growth, ZnO NWs of approximately 90 nm in diameter and  $1\ \mu\text{m}$  in length were branched to the  $\text{TiO}_2$  NW backbones. As a result, a denser micro-nanoscale NW structure was obtained as shown in figure 2b. Compared to the 1D  $\text{TiO}_2$  nanowire network, micro-nanoscale hierarchical  $\text{ZnO@TiO}_2$  NW structure possessed larger effective surface area, which may be important in amplifying the wetting behaviour according to the Wenzel model, or may entrap air pockets to support liquids according to the Cassie–Baxter model. The as-fabricated hierarchical NW network presented microscale roughness resulting from the underlying  $\text{TiO}_2$  NW backbone as well as nanoscale features from the ZnO nanopikes. The hierarchical network showed a highly homogeneous morphology across the whole surface with few defects. In figure 2c, control sample of well-aligned ZnO NW were produced, where the ZnO NWs with diameter of 100 nm and length of  $3\ \mu\text{m}$  were grown densely and vertically on substrate surface. In contrast to the hierarchical  $\text{ZnO@TiO}_2$  NW which consisted of both microscale roughness and nanoscale features, the top surface of the densely packed and vertically aligned ZnO NWs only presented nanoscale feature.

Figure 3a,b illustrates the advantages of using NWs as microscale templates for hierarchical structure fabrication compared to conventional microspheres. The  $\text{TiO}_2$  NWs were in micro-level length and nano-scale diameter. Compared to microspheres, NWs have larger effective area for contacting with the substrate or other NWs, which is favourable for NWs to form a robust network film with smaller variation on surface roughness. This is in contrast to using microspheres or micropowders as microscale templates, where microparticles tended to induce large variations in surface roughness and form defects on the surface. For example, as shown in figure 3c, microspheres were stacked on substrate and ZnO nanopikes were fabricated on their surface through hydrothermal reaction. However, microscale defects or vacancies as presented were unavoidable due to imperfect covering of microspheres on the






**Figure 3.** (a,b) Illustrations of micro-nanoscale hierarchical structure construction using (a) microspheres or (b) nanowires as micro-scale templates. (c) SEM images of microsphere layers prepared via drop-casting, and the micro-nano hierarchical structure fabricated based on the microsphere templates. Large surface defects and a greatly varied surface roughness were observed. (d) SEM images of micropowder layers prepared via drop-casting, and the micro-nano hierarchical structure fabricated based on the micropowder templates. Large surface defects and a greatly varied surface roughness were observed. (e) Micro-nano hierarchical structure fabricated based on the TiO<sub>2</sub> NW templates. Homogeneous surface topography and roughness were observed.

substrate surface. Similar results were also observed for irregular micropowders (figure 3d), where uneven layers of micropowders were formed on the substrate. Though ZnO nanopikes could be produced on the micropowder surface, the micro-nanoscale features had large variations among different areas due to the unevenness of the underlying micropowder layers. Instead, by employing TiO<sub>2</sub> NWs for constructing microscale topography of the underlying layer, the NWs exhibited a relatively homogeneous morphology at different locations. This resulted in a hierarchical NW network with less variation on surface roughness after the TiO<sub>2</sub> NW backbones were branched by secondary ZnO nanopikes (figure 3e).

To achieve desirable water-repelling property, samples were further modified to be superhydrophobic by conjugating fluorinated silane (perfluorooctyltriethoxysilane [28,34,40]) on the surface to form a chemically bonded low surface energy layer. Briefly, the surface of ZnO@TiO<sub>2</sub> NWs were coated with perfluorooctyltriethoxysilane using vapour-phase deposition by placing the samples in a vacuum desiccator overnight together with open glass vials containing perfluorooctyltriethoxysilane. After reaction the samples were calcinated at 120°C for 10 min. Similar fluorination process was conducted on control samples including vertical ZnO NWs as well as flat Si substrate. X-ray photoelectron spectroscopy (XPS) was carried out to verify the presence of the fluorinated coating. The pronounced F peaks in figure 4a confirmed successful fluorination for both hierarchical ZnO@TiO<sub>2</sub> NWs and ZnO NWs.


Contact angle (CA) measurements were performed to investigate the wetting properties of hierarchical ZnO@TiO<sub>2</sub> NW structure after fluorination. Figure 4b demonstrates the static CAs of water drops on different samples, including fluorinated ZnO@TiO<sub>2</sub> NW coating (ZnO@TiO<sub>2</sub> NWs-F), fluorinated vertical ZnO NWs (ZnO NWs-F), and fluorinated flat Si substrate as controls. The



**Figure 4.** (a) XPS spectra of fluorinated hierarchical ZnO@TiO<sub>2</sub> NWs-F film and vertical ZnO NWs-F. (b) Optical images and statistical results of the static contact angles of water on different fluorinated surfaces including ZnO@TiO<sub>2</sub> NWs-F coating, vertical ZnO NWs-F and fluorinated flat substrate (Flat-F). (c) Water repellent test on ZnO@TiO<sub>2</sub> NWs-F and vertical ZnO NWs-F. Time-resolved images of bouncing experiment for 5  $\mu$ l water drops on ZnO@TiO<sub>2</sub> NWs-F and vertical ZnO NWs-F are shown.

fluorinated hierarchical ZnO/TiO<sub>2</sub> surface exhibited high CA of  $159 \pm 3^\circ$ . On the other hand, the contact angles of control samples were much lower, where the CAs were  $103 \pm 5^\circ$  and  $68 \pm 1^\circ$  for fluorinated vertical ZnO NWs and flat substrate respectively. Bouncing behaviour of water droplets was further examined on different structured surfaces in order to evaluate the water-repelling property (figure 4c). Water droplets could readily bounce off the hierarchical ZnO@TiO<sub>2</sub> NWs-F surface, indicating the ZnO@TiO<sub>2</sub> NWs-F coating was highly repellent to water. In contrast, water drops could not bounce on fluorinated vertical ZnO NWs as well as fluorinated substrate surface, suggesting that the presence of micro-nanoscale features was essential for the surface to possess water-repellent property. These results were consistent with previous reports that micro-nanoscale topography significantly contributes to the superhydrophobic performance of surface [36,41,42]. In our case, the coupling of ZnO nanospikes with the underlying NW microtopography greatly increased the hydrophobicity of the surface compared to the ZnO NWs with nanoscale topography alone.

The wetting property of a surface is highly dependent on its surface topography and surface energy. For vertical ZnO NWs-F array, though fluorination substantially reduced the surface energy, it is still insufficient to achieve superhydrophobicity since the water drops could readily penetrate into the grooves between the NWs through capillary action. In contrast, the larger microscale structure provided by TiO<sub>2</sub> NWs coupled with the ZnO sub-NWs may amplify the superhydrophobic effects according to the Wenzel state, or air is likely to be entrapped more effectively by these nanowire branches according to the Cassie–Baxter model, which may prevent liquid permeation and contribute to the enhanced non-wetting properties. The coexistence of microscale topography and nanoscale feature of ZnO@TiO<sub>2</sub> NW resulted in different behaviours of water drops impacting on hierarchical ZnO@TiO<sub>2</sub> NWs-F and vertical



**Figure 5.** (a) Optical images and statistical results of the static contact angles of cell medium on different fluorinated surfaces including hierarchical ZnO@TiO<sub>2</sub> NWs-F coating, vertical ZnO NWs-F and Flat-F. (b) Optical images of blood and oil drops on hierarchical ZnO@TiO<sub>2</sub> NWs-F film and vertical ZnO NWs-F.

ZnO NWs-F surfaces, which was in agreement with previous studies that have shown hierarchical structure was critical for water-repellent properties.

In addition to water, the wetting behaviours of a series of liquids including cell culture medium, blood and corn oil were analysed on the samples (figure 5). Static contact angles of cell medium droplets on fluorinated ZnO@TiO<sub>2</sub> NW network, fluorinated vertical ZnO NW array and fluorinated flat substrate were measured to be 139 ± 2°, 111 ± 1° and 71 ± 1°, respectively. These results indicate that the ZnO@TiO<sub>2</sub> NWs-F coating was nearly superhydrophobic to bio-fluids which contain complex molecules such as proteins and other organic molecules. In addition, the contact angles of blood as well as corn oil were tested on the samples. Due to the lower surface tension of blood and oil droplets, these liquids tend to contaminate surface easily and have lower values of contact angle to many existing surfaces. The ZnO@TiO<sub>2</sub> NWs-F coating displayed contact angles of 89.9 ± 1.3° to blood and 41.2 ± 1.3° to corn oil, which were significantly higher than those on fluorinated ZnO NWs where the contact angles were 41.2 ± 1.3° to blood and 11.7 ± 3.8° to corn oil. Although the surface energy of ZnO@TiO<sub>2</sub> NWs-F coating was not sufficiently low to repel blood and corn oil, their contact angles were significantly higher than those on fluorinated ZnO NWs, thus confirming the ZnO@TiO<sub>2</sub> NWs-F coating was much more hydrophobic owing to the co-presence of microscale and nanoscale features.

### 3. Conclusion

In summary, using one-dimensional TiO<sub>2</sub> NWs as microscale templates, micro-nanoscale hierarchical nanowire network with excellent water-repelling property was successfully developed. TiO<sub>2</sub> NWs of micrometres length not only provided sufficient contact area with the substrate or NWs entangling for producing a robust network film but also served as excellent backbone structure for ZnO NW branches growth. The hierarchical structure exhibited water-repelling properties after surface modification, displaying excellent superhydrophobicity compared to flat substrate or vertical ZnO NW substrate

without hierarchical micro-nanoscale structure. This hierarchical nanowire-based superhydrophobic coating possessed homogeneous morphology in contrast to conventional microparticles/powders-based micro-nanoscale structure where significant surface defects or vacancies were present due to highly varied surface morphologies. Our work provides a promising approach of designing hierarchical nanowire film structure that offers great superhydrophobicity, which is a versatile approach for the coating of a wide range of materials to be self-cleaning.

**Data accessibility.** Supporting data are available as electronic supplementary material.

**Authors' contributions.** T.H., H.-J.C and J.T. carried out the experimental work, S.X. and C.D.Y. participated in data analysis, X.X. conceived of the study, B.-r.Y, H.-p.S., M.C. and C.L. designed and coordinated the study, T.H., H.-J.C. and X.X. drafted the manuscript. All authors gave final approval for publication.

**Competing interests.** We declare we have no competing interests.

**Funding.** X.X. would like to thank the Youth 1000 Talents Program of China and 100 Talents Program of Sun Yat-sen University (76120-18821104) for supports. T.H., X.X. and J.T. wish to acknowledge the financial support from the National Natural Science Foundation of China (grant nos. 51705543, 61771498 and 31530023).

**Acknowledgements.** The authors gratefully acknowledge Dr Gen He and Dr Fanmao Liu for their valuable supports to this project.

## References

- Xu Q, Zhang W, Dong C, Sreepasad TS, Xia Z. 2016 Biomimetic self-cleaning surfaces: synthesis, mechanism and applications. *J. R. Soc. Interface* **13**, 20160300. (doi:10.1098/rsif.2016.0300)
- Bhushan B, Jung YC, Koch K. 2009 Micro-, nano- and hierarchical structures for superhydrophobicity, self-cleaning and low adhesion. *Phil. Trans. R. Soc. A* **367**, 1631–1672. (doi:10.1098/rsta.2009.0014)
- Liu KS, Jiang L. 2012 Bio-inspired self-cleaning surfaces. *Materials Research* **42**, 231–263. (doi:10.1146/annurev-matsci-070511-155046)
- Cao CY *et al.* 2016 Robust fluorine-free superhydrophobic PDMS-ormosil@fabrics for highly effective self-cleaning and efficient oil-water separation. *J. Mater. Chem. A* **4**, 12 179–12 187. (doi:10.1039/c6ta04420d)
- Li S *et al.* 2015 Robust flower-like TiO<sub>2</sub>@Cotton fabrics with special wettability for effective self-cleaning and versatile oil/water separation. *Adv. Mater. Interfaces* **2**, 1500220. (doi:10.1002/admi.201500220)
- Zhang P, Lin L, Zang D, Guo X, Liu M. 2017 Designing bioinspired anti-biofouling surfaces based on a superwettability strategy. *Small* **13**, 1503334. (doi:10.1002/smll.201503334)
- Wang P, Zhang D, Lu Z. 2015 Slippery liquid-infused porous surface bio-inspired by pitcher plant for marine anti-biofouling application. *Colloids Surf. B Biointerfaces* **136**, 240–247. (doi:10.1016/j.colsurfb.2015.09.019)
- Zhang X, Li Z, Liu K, Jiang L. 2013 Bioinspired multifunctional foam with self-cleaning and oil/water separation. *Adv. Funct. Mater.* **23**, 2881–2886. (doi:10.1002/adfm.201202662)
- Teisala H, Tuominen M, Kuusipalo J. 2014 Superhydrophobic coatings on cellulose-based materials: fabrication, properties, and applications. *Adv. Mater. Interfaces* **1**, 1300026. (doi:10.1002/admi.201300026)
- Li Y, Chen S, Wu M, Sun J. 2014 All spraying processes for the fabrication of robust, self-healing, superhydrophobic coatings. *Adv. Mater.* **26**, 3344–3348. (doi:10.1002/adma.201306136)
- Manna U, Lynn DM. 2013 Restoration of superhydrophobicity in crushed polymer films by treatment with water: self-healing and recovery of damaged topographic features aided by an unlikely source. *Adv. Mater.* **25**, 5104–5108. (doi:10.1002/adma.201302217)
- You I, Lee TG, Nam YS, Lee H. 2014 Fabrication of a Micro-omnifluidic device by omniphilic/omniphobic patterning on nanostructured surfaces. *ACS Nano* **8**, 9016–9024. (doi:10.1021/nl502226v)
- Yun Z, Minglie Q, Anjie W, Dongpyo K. 2013 Bioinspired superhydrophobic carbonaceous hairy microstructures with strong water adhesion and high gas retaining capability. *Adv. Mater.* **25**, 4561–4565. (doi:10.1002/adma.201300858)
- Neinhuis C, Barthlott W. 1997 Characterization and distribution of water-repellent, self-cleaning plant surfaces. *Ann. Bot.* **79**, 667–677. (doi:10.1006/anbo.1997.0400)
- Bae WG, Kim HN, Kim D, Park SH, Jeong HE, Suh KY. 2014 25th Anniversary article: scalable multiscale patterned structures inspired by nature: the role of hierarchy. *Adv. Mater.* **26**, 675–699. (doi:10.1002/adma.201303412)
- Wenzel RN. 1936 Resistance of solid surfaces to wetting by water. *Ind. Eng. Chem.* **28**, 988–994. (doi:10.1021/ie50320a024)
- Cassie ABD, Baxter S. 1944 Wettability of porous surfaces. *Trans. Faraday Soc.* **40**, 546–551. (doi:10.1039/TF9444000546)
- Wang MF, Raghunathan N, Ziaie B. 2007 A nonlithographic top-down electrochemical approach for creating hierarchical (micro-nano) superhydrophobic silicon surfaces. *Langmuir* **23**, 2300–2303. (doi:10.1021/la0632301)
- Li Y, Zheng M, Ma L, Zhong M, Shen W. 2008 Fabrication of hierarchical ZnO architectures and their superhydrophobic surfaces with strong adhesive force. *Inorg. Chem.* **47**, 3140–3143. (doi:10.1021/ic7021598)
- Xiong J, Das SN, Shin B, Kar JP, Choi JH, Myoung JM. 2010 Biomimetic hierarchical ZnO structure with superhydrophobic and antireflective properties. *J. Colloid Interface Sci.* **350**, 344–347. (doi:10.1016/j.jcis.2010.06.053)
- Xie X, Aalipour A, Gupta SV, Melosh NA. 2015 Determining the time window for dynamic nanowire cell penetration processes. *ACS Nano* **9**, 11 667–11 677. (doi:10.1021/acsnano.5b05498)
- Xie X, Xu AM, Angle MR, Tayebi N, Verma P, Melosh NA. 2013 Mechanical model of vertical nanowire cell penetration. *Nano Lett.* **13**, 6002–6008. (doi:10.1021/nl403201a)
- Xie X, Xu AM, Leal-Ortiz S, Cao YH, Garner CC, Melosh NA. 2013 Nanostraw-electroporation system for highly efficient intracellular delivery and transfection. *ACS Nano* **7**, 4351–4358. (doi:10.1021/nn400874a)
- Barthwal S, Kim YS, Lim S-H. 2013 Mechanically robust superamphiphobic aluminum surface with nanopore-embedded microtexture. *Langmuir* **29**, 11 966–11 974. (doi:10.1021/la402600h)
- Kim D-H, Kim Y, Kang J-W, Hong S, Lee D, Cho C-R, Kim S-H, Lee D-W, Kim J-M. 2011 Inclined-wall regular micro-pillar-arrayed surfaces covered entirely with an alumina nanowire forest and their improved superhydrophobicity. *J. Micromech. Microeng.* **21**, 075024. (doi:10.1088/0960-1317/21/7/075024)
- Myint MTZ, Kitsomboonloha R, Baruah S, Dutta J. 2011 Superhydrophobic surfaces using selected zinc oxide microrod growth on ink-jetted patterns. *J. Colloid Interface Sci.* **354**, 810–815. (doi:10.1016/j.jcis.2010.11.004)
- Park HK, Yoon SW, Do YR. 2012 Superhydrophobicity of 2D SiO<sub>2</sub> hierarchical micro/nanorod structures fabricated using a two-step micro/nanosphere lithography. *J. Mater. Chem.* **22**, 14 035–14 041. (doi:10.1039/c2jm31978k)
- Sun Z, Liao T, Liu K, Jiang L, Kim JH, Dou SX. 2013 Robust superhydrophobicity of hierarchical ZnO hollow microspheres fabricated by two-step self-assembly. *Nano Res.* **6**, 726–735. (doi:10.1007/s12274-013-0350-6)
- Li Y, Huang XJ, Heo SH, Li CC, Choi YK, Cai WP, Cho SO. 2007 Superhydrophobic bionic surfaces with hierarchical microsphere/SWCNT composite arrays. *Langmuir* **23**, 2169–2174. (doi:10.1021/la0620758)
- Yang H, Dou X, Fang Y, Jiang P. 2013 Self-assembled biomimetic superhydrophobic hierarchical arrays. *J. Colloid Interface Sci.* **405**, 51–57. (doi:10.1016/j.jcis.2013.05.040)
- Deng X, Mammen L, Butt HJ, Vollmer D. 2012 Candle soot as a template for a transparent robust



- superamphiphobic coating. *Science* **335**, 67–70. (doi:10.1126/science.1207115)
32. Karthik N, Sethuraman MG. 2015 Fabrication of micro-nanocomposite coatings with lotus leaf like texture by combining electroless and candle soot depositions. *New J. Chem.* **39**, 3337–3340. (doi:10.1039/c4nj02380c)
  33. Kandjani AE, Sabri YM, Field MR, Coyle VE, Smith R, Bhargava SK. 2016 Candle-soot derived photoactive and superamphiphobic fractal titania electrode. *Chem. Mater.* **28**, 7919–7927. (doi:10.1021/acs.chemmater.6b03537)
  34. Lu Y, Sathasivam S, Song J, Crick CR, Carmalt CJ, Parkin IP. 2015 Robust self-cleaning surfaces that function when exposed to either air or oil. *Science* **347**, 1132–1135. (doi:10.1126/science.aaa0946)
  35. Campbell JL, Breedon M, Latham K, Kalantar-Zadeh K. 2008 Electrowetting of superhydrophobic ZnO nanorods. *Langmuir* **24**, 5091–5098. (doi:10.1021/la7030413)
  36. Bielinski AR, Boban B, He Y, Kazyak E, Lee DH, Wang C, Tuteja A, Dasgupta NP. 2017 Rational design of hyperbranched nanowire systems for tunable superomniphobic surfaces enabled by atomic layer deposition. *ACS Nano* **11**, 478–489. (doi:10.1021/acs.nano.6b06463)
  37. Liu Y, Chen W, Wei S, Gao W. 2014 TiO<sub>2</sub>/ZnO nanocomposite, ZnO/ZnO bi-level nanostructure and ZnO nanorod arrays: microstructure and time-affected wettability change in ambient conditions. *RSC Adv.* **4**, 30 658–30 665. (doi:10.1039/c4ra04904g)
  38. Jitputti J, Suzuki Y, Yoshikawa S. 2008 Synthesis of TiO<sub>2</sub> nanowires and their photocatalytic activity for hydrogen evolution. *Catal. Commun.* **9**, 1265–1271. (doi:10.1016/j.catcom.2007.11.016)
  39. Xie X, Melosh NA. 2015 Fabrication of sub-cell size ‘spiky’ nanoparticles and their interfaces with biological cells. *J. Biomed. Mater. Res. B* **3**, 5155–5160. (doi:10.1039/c5tb00452g)
  40. Lai Y, Gao X, Zhuang H, Huang J, Lin C, Jiang L. 2009 Designing superhydrophobic porous nanostructures with tunable water adhesion. *Adv. Mater.* **21**, 3799–3803. (doi:10.1002/adma.200900686)
  41. Cao Y, Yuan L, Hu B, Zhou J. 2015 Three-tier rough superhydrophobic surfaces. *Nanotechnology* **26**, 315705. (doi:10.1088/0957-4484/26/31/315705)
  42. Zhang S, Huang J, Tang Y, Li S, Ge M, Chen Z, Zhang K, Lai Y. 2016 Understanding the role of dynamic wettability for condensate microdrop self-propelling based on designed superhydrophobic TiO<sub>2</sub> nanostructures. *Small* **13**, 1600687. (doi:10.1002/smll.201600687)